

## 95/5 (Clean 'n Brite™ 95/5)

### ***NOMINAL COMPOSITION***

Tin	95% ± 1.0%	Lead	0.2% Max	Arsenic	0.05% Max
Antimony	4.5% –5.5%	Cadmium	0.005% Max	Iron	0.04% Max
Copper	0.08% Max	Aluminum	0.005% Max	Zinc	0.005% Max
Silver	0.015% Max	Bismuth	0.15% Max		

### ***PHYSICAL PROPERTIES***

Color	White
Melting Point (Solidus)	450°F (233°C)
Flow Point (Liquidus)	464°F (240°C)
Specific Gravity	7.28
Density (Lbs/in <sup>3</sup> )	0.263
Electrical Conductivity (%IACS)	N/A
Electrical Resistivity (Microhm-cm)	N/A
Bulk Room Temperature Tensile Strength (PSI)	6,400

\*IACS = International Annealed Copper Standard

### ***SOLDERING CHARACTERISTICS***

95/5 is a general purpose solder used in applications involving soldering of copper and copper alloys and/or ferrous base alloys where use of lead containing solder is not permitted. This soft solder may be used in applications involving higher service temperatures. Typical applications for this alloy include copper components in air conditioning industry. This alloy is also recommended in applications involving food handling or drinking water components where use of lead containing alloys is not permitted. Antimony bearing alloys are not recommended in soldering of brass parts due to formation of brittle Sb-Zn intermetallics.

### ***PROPERTIES OF SOLDER JOINTS***

The properties of a soldered joint are dependent upon numerous factors including base metal properties, joint design, metallurgical interaction between the base metal and the filler metal.

### ***AVAILABLE FORMS***

Wire, engineered preforms, specialty preforms per customer specification, powder and paste.

### ***SPECIFICATIONS***

95/5 alloy conforms to the following specifications:

- American Society for Testing and Materials (ASTM) B32 Sb5

### ***APPLICABLE PRODUCT CODE(S)***

---

The applicable Lucas-Milhaupt product code(s) for this technical data sheet: A00000410, Legacy Codes: 63-950, 29777, 33673 (Acid Core), 35317 (Organic Core).

Distribution P/N: 57263.

### ***SAFETY INFORMATION***

---

The operation and maintenance of brazing equipment or facility should conform to the provisions of American National Standard (ANSI) Z49.1, "Safety in Welding and Cutting". For more complete information refer to the Material Safety Data Sheet for 95/5.

### ***WARRANTY CLAUSE***

---

Lucas-Milhaupt, Inc. believes the information contained herein to be reliable. However, the information is given by Lucas-Milhaupt, Inc. without charge and the user shall use such information at its own discretion and risk. This information is provided on an "AS IS" AND "AS AVAILABLE" basis and Lucas-Milhaupt, Inc. specifically disclaims warranties of any kind, either express or implied, including, but not limited to, warranties of title or implied warranties of merchantability or fitness for a particular purpose. No oral advice or written or electronically delivered information given by Lucas-Milhaupt, Inc. or any of its officers, directors, employees, or agents shall create any warranty. Lucas-Milhaupt, Inc. assumes no responsibility for results obtained or damages incurred from the use of such information in whole or in part.